

spec

Fabric grades:

Bravo II GR3

Canter GR1



Bravo II Graystone



Canter Quarry



Sand



Maize



Toasty



Saddle



Tumbleweed



Hematite



Lucid



Pyrite



Safari



Thatch



Saddle



Twilight



Baltic



Alfalfa



Earth



Tango



Clay



Dusk



Ballad



Willow



Tusk



Ancho



Driftwood



Night



Ink



Storm



Bordeaux



Chestnut



Cinder



Mica



Night



Iron



Mica



Brazen



Black



Iron



Basalt



Tawny



Sable



Onyx

Reduced Environmental Impact
PVC Free

from Momentum Textiles

Technical Information

	Width - Pattern	Content	Abrasion	Light Fastness	Approximate Repeats	Notes
Polyurethane PVC Free Cleaning Code: L A.C.T.:	54" BRAVO II	100% Polyurethane / PVC Free	500,000 D.R.	200 Hrs. Class 4.5		Diluted Bleach Cleanable (4:1)
	54" CANTER	100% Polyurethane / PVC Free	240,000 D.R.	40 Hrs. Class 4.5		Diluted Bleach Cleanable (4:1)

EXPLANATION OF ACT ICONS UPHOLSTERY

Fire Retardancy

Flammability testing determined as fabric's resistance to burning.



PASSES
California 117

Colorfastness to Wet & Dry Crocking

Colorfastness to wet & dry crocking refers to the rubbing off of color from the fabric onto clothing, hands or other material and can occur under wet or dry conditions.



PASSES
AATCC 8-1974 Dry Crocking, Class 4 minimum; Wet Crocking,
Class 3 minimum.

Colorfastness to Light

Colorfastness to light is the degree to which the fabric will retain its color when exposed to light.



PASSES
AATCC 16A-1974 or AATCC 16E-1976; Class 4 minimum at 40 hours.
NOTE: Class 4 minimum at 60 hours is recommended for direct sunlight
exposure situations.

Physical Properties

3 physical property tests include: brush pill test to determine a fabric's pilling. Breaking/tensile strength is the ability of a fabric to withstand tension without breaking or tearing. Seam slippage is the pulling apart of the fabrics at the seams.



PASSES
Brush Pill ASTM D3511, 3-4 minimum.
Breaking Strength ASTM D3597-D1682-64 (1975) 50 lbs. minimum
in warp & weft.
Seam Slippage ASTM D3597-D434-75 25 lbs. minimum in warp & weft.

Abrasion

Abrasion is the ability of a fabric to withstand damage from wear and rubbing. There is a general contract specification as well as a heavy duty specification.

PASSES



General Contract ASTM 3597 modified (#10 cotton duck);
15,000 double rubs Wyzenbeek Method.



Heavy Duty ASTM 3597 modified (#10 cotton duck); 30,000 double rubs
Wyzenbeek Method or ASTM D4966 (with 21 oz. weight);
40,000 rubs Martindale Method.

Cleaning Code Definition

L: Clean with warm water and mild soap, using clean cloth, as soon as possible.

spec

SPEC FURNITURE INC.
Toll Free: 888.761.7732
Tel: 416.246.5550
Fax: 416.246.5549
email: specit@specfurniture.com
www.specfurniture.com